

Technical Data

JOTASHIELD TEX MEDIUM



Product description

Jotashield Tex Medium is a satin finish Medium Textured decorative paint containing a tough flexible 100% pure acrylic water based binder and rock hard aggregates.

Recommended use

For use on exterior surfaces of cement plaster, concrete, bricks, masonry. The product has very good adhesion properties as well as good weather and water resistance. Jotashield Tex Medium when applied with a sponge roller provides an attractive texture that can hide and cover minor imperfections in the surface. The Product has been independently tested at the Taywood Engineering lab in UK to have crack bridging up to 0.7 mm and is also tested for Carbon Dioxide diffusion, Water Vapour Transmission and Liquid Water Transmission.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)			
Film thickness, wet (μm)			
Theoretical spreading rate (m^2/l)	2	4	3

Comments

Film thickness will vary and are calculated as an average. Spreading rates depend on type of texture, surface porosity, imperfections, wastage during application etc.

Physical properties

Colour	Refer to the Jotashield Exterior Colour fan.
Solids (vol %)*	49 \pm 2

*Measured according to ISO 3233:1998 (E)

Surface preparation

The substrate must be sound, clean, dry, free from dust, oil, grease and laitance etc. All traces of release agents must be removed. On chalky and dusty surfaces, all loose material must be removed by stiff bristle brushing.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be min. 10°C and min. 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate.

Application methods

Spray	Hopper Gun.
Brush	Recommended.
Roller	Recommended.

Application data

Thinner/Cleaner Water

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate
- * Relative humidity 70%

Substrate temperature	10°C	23°C	40°C
Surface dry	6 h	3 h	1 h
Through dry	10 h	5 h	3 h
Dry to recoat, minimum ¹	10 h	5 h	3 h
Dry to recoat, maximum ^{2,3}			

1. Recommended data given for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied – reference is made to the corresponding system data sheet.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotashield Penetrating Primer or Alkali Resistant Primer	1 coat
Jotashield Tex Medium	2 coats

If any exterior Block filler is used to rectify imperfections on the substrate, proper sanding followed by a full undiluted coat of Penetrating Sealer must be used before applying any Jotashield topcoats.

Other systems may be specified, depending on area of use

Test Certificates

Determination of Crack Bridging Ability - Performed by Taywood Engineering, UK.
Determination of Moisture Vapour Transmission Rate - Performed by Taywood Engineering, UK.
Determination of Carbon Dioxide Diffusion Resistance - Performed by Taywood Engineering, UK.
Determination of Liquid Water Transmission Rate - Performed by Taywood Engineering, UK.

Storage

The product must be stored in accordance with national regulations. The product must be kept in a cool and well-ventilated place, protected from heat and direct sunlight. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

1 US G and 5 US G.

Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Head Office & Nordic	Europe	Middle East	South East Asia
Jotun Paints	Jotun Paints (Europe) Ltd.	Jotun U.A.E Ltd. LLC.	Jotun (Singapore) Pte. Ltd.
P.O. Box 2021	Stather Road, Flixborough		No 11-15, Sixth Lok Yang
N-3248 Sandefjord	North Lincolnshire DN15	Al Quoz Industrial Area	Road
Norway	8RR	P.O Box 3671	Jurong
Phone +47 33 45 70 00	United Kingdom	Dubai U.A.E	Singapore 628 111
Fax +47 33 46 46 13	Phone +44 172 44 00 000	Phone +971 4 3 39 50 00	Phone +65 6265 4711
	Fax +44 172 44 00 100	Fax +971 4 3 38 06 66	Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 18 NOVEMBER 2002 BY JOTUN PAINTS
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED